

## TABLA DE REFERENCIA DE MATERIALES

### MATERIAL REFERENCE CHART

MATERIAL	Forgings	Castings	Wrought Fittings
Carbon Steel Cold Temperature Service	A105 A350-LF2	A216-WCB	A234-WPB A420-WPL6
Carbon-1/2 Molybdenum Alloy Steel High Temperature Service	A182-F1	A217-WC1 A352-LC1	A234-WP1
3-1/2 Nickel Alloy Steel Low Temperature Service	A350-LF3	A352-LC3	A420-WPL3
1/2 Cr-1/2 Mo Alloy Steel 1/2 Cr-1/2 Mo-1 Ni Alloy 3/4 Cr-1 Mo-3/4 Ni Alloy Steel 1 Cr-1/2 Mo Alloy Steel	A182-F2  A182-F12 CL2	A217-WC4 A217-WC5	A234-WP12 CL2
1-1/4 Cr-1/2 Mo Alloy Steel 2-1/4 Cr-1 Mo Alloy Steel 5 Cr-1/2 Mo Alloy Steel 5 Cr-1/2 Mo Alloy Steel 9 Cr-1 Mo Alloy Steel 13 Cr Alloy Steel	A182-F11 CL2 A182-F22 CL3 A182-F5 A182-F5a A182-F9 A182-F6	A217-WC6 A217-WC9  A217-C5 A217-C12 A743-CA15	A234-WP11 CL2 A234-WP22 CL3 A234-WP5  A234-WP9
Type 304 Stainless Steel (18 Cr-8 Ni) Standard Low Carbon High Temperature Service	A182-F304 A182-F304L A182-F304H	A351-CF3  A351-CF8	A403-WP304 A403-WP304L A403-WP304H
Type 310 Stainless Steel (25 Cr-20 Ni) Type 316 Stainless Steel (16 Cr-12 Ni-2 Mo) Standard Low Carbon High Temperature	A182-F310H  A182-F316 A182-F316L A182-F316H	A351-CK20  A351-CF3M A351-CF8M	A403-WP310  A403-WP316 A403-WP316L A403-WP316H
Type 317 Stainless Steel (18 Cr-13 Ni-3 Mo) Type 321 Stainless Steel (18 Cr-10 Ni-Ti)			A403-WP317

\*\* COLVAPOR no acepta responsabilidad por la precisión o validez de ésta información.

\*\* COLVAPOR accepts no responsibility for the accuracy or validity of this data.

<b>MATERIAL</b>	<b>Forgings</b>	<b>Castings</b>	<b>Wrought Fittings</b>
Standard High Temperature Service	A182-F321 A182-F321H		A403-WP321 A403-WP321H
Type 347 Stainless Steel (18 Cr-10 Ni-Cb) Standard High Temperature Service	A182-F347 A182-F347H	A351-CF8C	A403-WP347 A403-WP347H
Type 348 Stainless Steel (18 Cr-10 Ni-Cb) Standard High Temperature Service	A182-F348 A182-F348H		A403-WP348 A403-WP438H

\*\* COLVAPOR no acepta responsabilidad por la precisión o validez de ésta información.

\*\* COLVAPOR accepts no responsibility for the accuracy or validity of this data.